



Kraft

ProVantage KraftTop Liner TYPICAL VALUES

Parameter	Test method	Unit of measure	Substance (g/m ²)												
			100	110	115	120	125	135	140	150	160	170	175	186	200
Moisture _(average)	ISO 287	%	7.8												
Bursting strength	ISO 2758	kPa	410	455	470	485	500	530	545	570	595	610	630	650	680
SCT _{CD}	ISO 9895	kN/m	1.8	2.0	2.1	2.2	2.3	2.4	2.5	2.65	2.8	2.9	3.0	3.2	3.4
Cobb ₆₀ (top)	ISO 535	g/m ²	30												

Certificates

- ISEGA
- ISO 9001
- ISO 14001
- OHSAS 18001
- FSC® CoC
- PEFC™
- EN 13432

Typical values after conditioning measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Valid until: 31.12.2018

IN TOUCH EVERY DAY

www.mondigroup.com

Technical Customer Service

Mondi Štětí a.s.

Litoměřická 272

411 08 Štětí, Czech Republic

Tel: +420 416 802 603